

Bicor™ 70 HBS-2

Oriented Polypropylene Film


Jindal
Films

Product Description

Bicor HBS-2 is a one-side sealable, one-side high barrier PVdC-coated OPP film designed for use as the inside sealant web in high-barrier laminations.

Key Features

- Excellent moisture and oxygen barriers
- Excellent flavor and aroma barrier
- Excellent sealability, hot tack, and seal range
- Lap sealable to a coex outer web



General

Availability

- ✓ Latin America
- ✓ North America
- ✓ South America

Features

- ✓ Flavor & Aroma Barrier
- ✓ In Lamination Lap Sealable
- ✓ Gas Barrier
- ✓ Moisture Barrier
- ✓ Oxygen Barrier
- ✓ PVdC Coated
- ✓ High Barrier PVdC Coated

Applications

- ✓ Biscuits/Cookie/Crackers
- ✓ Confectionery, Sugar
- ✓ Bakery
- ✓ Crisps and Snacks

Uses

- ✓ HFFS Flexible Packaging
- ✓ Pre-made Bags - Flexible Packaging
- ✓ VFFS Flexible Packaging

Appearance

- ✓ Clear/Transparent

Processing Method

- ✓ Inner Web Adhesive Lamination
- ✓ Solvent Flexographic Printing
- ✓ Solvent Rotogravure Printing
- ✓ Inner Web Extrusion Lamination

Properties & Typical Values

Property	Typical Value	Unit	Test Based On
Yield	56.2	m ² /kg	Internal Method
Unit Weight	17.7	g/m ²	Internal Method
Film Thickness	18	µm	Internal Method
Haze	1.8	%	Internal Method
Tensile Strength at Break <i>510 mm/min pull rate, 50 mm jaw separation</i>			
MD	114	Mpa	Internal Method
TD	207	Mpa	Internal Method
Dimensional Stability 135°C / 275°F, 7 min			
MD	-4.5	%	Internal Method
TD	-4.0	%	Internal Method
Crimp Seal Strength 110°C, 0.1 Mpa, 0.75 sec			
	420	g/2.5 cm	Internal Method
Crimp Seal (MST)	91	°C	Internal Method
Water Vapor Transmission Rate 38°C, 90% RH			
	2.5	g/m ² /24 hr	Internal Method
Oxygen Transmission Rate 23°C, 0% RH			
	4.7	cm ³ /m ² /24 hr	Internal Method

TYPICAL PROPERTIES : these are not to be construed as specifications

Food Contact

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: <https://www.jindalfilms.com/login-register-docmg/>

Legal Statement

This product is not intended for or supported for use in pharmaceutical or medical applications requiring compliance with EU or US Pharmacopeia.

Processing Statement

- HBS-2 can be lap sealed to sealable coex OPP.
- In PE laminations, Jindal Films recommends retreating, priming, or an EMA/PE extrusion blend for improved bonds.
- HBS-2 can be used in HFFS and VFFS applications.

Footnotes

1. Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete country availability.
2. Tested at 38°C (100°F)/100%RH, then calculated to 90%RH with .90 multiplier.
3. Sample dimensions and conditioning vary due to differences in equipment design.

Revision date

- October 10, 2013

© 2023 Jindal Films. Jindal Films, Jindal Films, the Jindal Films' logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. Any data included herein may be based upon: analyses of representative samples and not the actual product shipped, typical values, or otherwise. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of any non-Jindal Films' product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "Jindal Films" and "Jindal" are each used for convenience, and may include Films Americas LLC, Jindal Films Americas LLC, Films Europe S.à.r.l., Jindal Films Virton SPRL, Jindal Films India Ltd., or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, some with names including "Jindal" or "Films" and some not. Neither these terms and conditions, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.