## Bicor™ 75ABX

Oriented Polypropylene Film


# **Jindal**

## **Product Description**

Bicor AB-X is a two-side coated, sealable OPP film designed for general use in many applications, including overwrap, horizontal, and vertical packaging. This film is suitable as an unsupported web or in a lamination. It can be surface printed, reverse printed, or used unprinted.

### **Key Features**

- · Outstanding optical properties
- · Robust machinability
- · Low and consistent COF
- Excellent hot slip
- · Excellent stiffness
- · Excellent flavor and aroma barrier
- Excellent hot tack and seal strength
- · Very broad seal range



## General

## Availability

Latin America

#### Features

Acrylic Coated

#### **Applications**

Biscuits/Cookie/Crackers

Confectionery, Sugar

#### Uses

Box Overwrap Flexible Packaging

Tobacco Overwrap Flexible Packaging

## Appearance

Clear/Transparent

#### **Processing Method**

Cold Seal Adhesive

Solvent Flexographic Printing

Water-based Flexographic Printing

North America

Flavor & Aroma Barrier

Box Overwrap

Tobacco

HFFS Flexible Packaging

VFFS Flexible Packaging

South America

In Lamination Lap Sealable

Confectionery, Gum

Pre-made Bags - Flexible Packaging

Inner Web Adhesive Lamination

Solvent Rotogravure Printing

Outer Web Adhesive Lamination

Surface Print Unsupported

#### **Properties & Typical Values**

Property	Typical Value Unit	Test Based On
Yield	56.9 m²/kg	Internal Method
Unit Weight	17.6 g/m²	Internal Method
Film Thickness	19 μm	Internal Method
Gloss (45°)	89 Gloss Unit	Internal Method
Haze	1.2 %	Internal Method
Tensile Strength at Break		
510 mm/min pull rate, 50 mm jaw separation		
MD	124 Mpa	Internal Method
TD	207 Mpa	Internal Method
Dimensional Stability 135°C / 275°F, 7 min		
MD	-4.5 %	Internal Method
TD	-4.0 %	Internal Method
Crimp Seal Strength		
127°C, 0.1 Mpa, 0.75 sec	510 g/2.5 cm	Internal Method
Crimp Seal (MST)	81 °C	Internal Method
Coefficient of Friction		
Acrylic/Acrylic	0.23	Internal Method
Water Vapor Transmission Rate		
38°C, 90% RH	8.2 g/m²/24 hr	Internal Method

#### TYPICAL PROPERTIES: these are not to be construed as specifications

#### **Food Contact**

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: <a href="https://www.jindalfilms.com/login-register-docmg/">https://www.jindalfilms.com/login-register-docmg/</a>

### **Legal Statement**

This product is not intended for or supported for use in pharmaceutical or medical applications requiring compliance with EU or US Pharmacopeia.

#### **Processing Statement**

- This film is designed for horizontal, vertical, and general overwrap applications.
- AB-X can be used as a monoweb or as the inner or outer web of a lamination.
- AB-X is lap sealable to other acrylic-coated and sealable PVdC-coated films.
- Acrylic coating and its properties can be affected by extreme humidity and water condensation. Thorough testing is recommended when considering acrylic-coated films in refrigerated or frozen applications.
- · Acrylic coating must be primed if used in extrusion laon lamination.
- Acrylic is an excellent surface for water-based or solvent-based inks, adhesives, and code-dating (cold wet or hot stamp)
  without treatment.
- -To avoid blocking, ghosting, high residual solvents, or decreased sealability, converters should eliminate the use of slow solvents (cellosolve, glycol ethers, MIBK, butanol, etc) when printing on acrylic surfaces. The use of esters should be minimized.

#### **Footnotes**

- 1. Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete country availability.
- 2. Tested at 38°C (100°F)/100%RH, then calculated to 90%RH with .90 multiplier.

#### **Revision date**

• July 20, 2022

© 2023 Jindal Films, Jindal Films, the Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information in may be based upon: analyses of representatives samples and not the actual product spined, projectly product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information, nor do we warrant, expressly or impliedly, the merchantality, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processed seconded. The user is solely responsible for all determinations regarding any use of material or product and any process in its expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or reliying on any of the information in this document. This document is not an endrosement of any one-based films products or process, and we expressly disclaim any contrary implication. The terms "we," "out," "Jindal Films Americas LLC, Films Europe S.ár.I., Jindal Films Virton SPRL, Jindal Films India Ltd., or any companies affiliated with them in the production and sale of film products. There are a number of sexponsibility for local action and accountability remains with them.