Metallyte™ 28UBWES

Oriented Polypropylene Film

Product Description

MetallyteTM UBWES is a multi-layer, cavitated, white OPP film with an enhanced sealant to allow sealing through contamination. This film has an exceptional barrier to gases, flavors, and moisture. It is metallized on one side with a proprietary sealant layer on the other. UBWES is lap sealable to other coextruded OPP films.

UBWES is used as the inner web for adhesive and extrusion laminations, where superior moisture and oxygen barriers are required. UBWES provides an excellent light barrier and is designed to provide strong, leak-free seals for flat pouches andhas been designed specifically to replace foil and a sealant web in those applications.

Vacuum White Opaque Multilayer Cavitated Polypropylene Core Enhanced Heat Sealable Layer

Inner Web Extrusion Lamination

Key Features

- · Exceptional seal strength
- Outstanding opacity
- Outstanding moisture and oxygen barrier
- Excellent aroma and flavor barrier
- Excellent flex-crack resistance
- Excellent hot tack

Surface Print Unsupported

Improved barrier to Mineral Oils compared to non-barrier film⁽¹⁾

Significant mineral oils contamination protection period of more than 2 years General Availability North America Latin America South America Africa & Middle East Asia Pacific Europe Features Flavor & Aroma Barrier 💙 In Lamination Lap Sealable Gas Barrier Light Barrier Moisture Barrier Oxygen Barrier **Applications** Ory Foods and Beverage Powders Uses HFFS Flexible Packaging VFFS Flexible Packaging Pre-made Bags - Flexible Packaging Pouches - Flexible Packaging Appearance Metallized - White **Processing Method** Inner Web Adhesive Lamination Solvent Flexographic Printing Solvent Rotogravure Printing

Water-based Flexographic Printing

Properties & Typical Values

Property	Typical Value Unit	Test Based On
Yield	48.4 m²/kg	Internal Method
Unit Weight	20.7 g/m ²	Internal Method
Film Thickness	28 μm	Internal Method
Optical Density	3.0	Internal Method
Tensile Strength at Break		
510 mm/min pull rate, 50 mm jaw separation		
MD	82.7 Mpa	Internal Method
TD	172 Mpa	Internal Method
Dimensional Stability 135°C / 275°F, 7 min		
MD	-5.0 %	Internal Method
TD	-3.0 %	Internal Method
Crimp Seal Strength Untreated/Untreated		
127°C, 0.1 Mpa, 0.75 sec	1500 g/2.5 cm	Internal Method
Untreated/Untreated		
99°C, 0.1 Mpa, 0.75 sec	690 g/2.5 cm	Internal Method
Minimum Sealing Temperature (Min 750g/25mm)		
Untreated/Untreated		
25N/cm2 - 0,5 sec - Flat/Flat	85 °C	Internal Method
Heat Seal Range (RDM)		
RDM – 750gr – single web – 25N/cm² – 0.5sec – flat/flat		
Untreated Surface	65 °C	Internal Method
Crimp Seal (MST)		
Untreated/Untreated	79 °C	Internal Method
Water Vapor Transmission Rate		
38°C, 90% RH	0.1 g/m²/24 hr	Internal Method
Oxygen Transmission Rate		
23°C, 0% RH	0.1 cm ³ /m ² /24 hr	Internal Method

TYPICAL PROPERTIES: these are not to be construed as specifications

Food Contact

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: https://www.jindalfilms.com/login-register-docmg/

Legal Statement

This product is not intended for or supported for use in pharmaceutical or medical applications requiring compliance with EU or US Pharmacopeia.

Processing Statement

- In-line treatment of the metalized surface is mandatory for converting.
- Contact your Jindal Films Technical Service Representative for processing recommendations and guidelines.

Footnotes

- 1. (1) Please contact your sales representative to get quantitative data on film barrier properties to Mineral Oils (MOSH and MOAH).
- 2. Please contact your Sales Representative for complete country availability.

Revision date

• March 28, 2024

© 2023 Jindal Films, Jindal Films, the Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footeds, and other included herein may be based upon, analyses of representative samples and not the accutal product synthesis, or otherwise. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, expressly or implicible, the merchanish lightly, titness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processed sectibled. The user is solely responsible for all determinations regarding any use of material or product and any process in its retritories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document is not an endrosement of any non-Jindal Films' product or process, and we expressly disclaim any contract yrimplication. The terms "we" "out," "lindal Films' are each used for convenience, and may include Films Americas LLC, Films Europe S.ár.I., Jindal Films Virton SPRL, Jindal Films India It.d., or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, some with names including "infindal" or "Films" and "Sindal" are each used for convenience, some