

Bicor™ 25MB400

Oriented Polypropylene Film




Product Description

Bicor™ MB400 is a heat sealable coextruded biaxially oriented polypropylene film that can be used on a wide range of packaging machines. MB400 can be either used as mono material or in laminated structures.

Key Features

- Outstanding optical properties
- Good seal strength
- Good dimensional stability
- Good hot slip
- Good hot tack



General

Availability

- ✓ Africa & Middle East
- ✓ Asia Pacific
- ✓ Europe

Features

- ✓ In Lamination Lap Sealable

Applications

- ✓ Biscuits/Cookie/Crackers
- ✓ Confectionery, Sugar
- ✓ Confectionery, Chocolate
- ✓ Household and Detergents
- ✓ Ice Cream
- ✓ Box Overwrap
- ✓ Bakery
- ✓ Frozen Food
- ✓ Crisps and Snacks
- ✓ Confectionery, Gum
- ✓ Fresh Produce
- ✓ Health and Beauty Care
- ✓ Pet Food

Uses

- ✓ HFFS Flexible Packaging
- ✓ Pre-made Bags - Flexible Packaging
- ✓ VFFS Flexible Packaging

Appearance

- ✓ Clear/Transparent

Processing Method

- ✓ Inner Web Adhesive Lamination
- ✓ Solvent Rotogravure Printing
- ✓ Outer Web Adhesive Lamination
- ✓ Surface Print Unsupported
- ✓ Solvent Flexographic Printing
- ✓ Outer Web Extrusion Lamination

Properties & Typical Values

Property	Typical Value	Unit	Test Based On
Yield	30900	in ² /lb	Internal Method
Unit Weight	14.0	lb/ream	Internal Method
Film Thickness	0.98	mil	Internal Method
Gloss (45°)	85	Gloss Unit	Internal Method
Haze	1.8	%	Internal Method
Tensile Strength at Break			
7.9 in/min pull rate, 4.9 in jaw separation			
MD	20300	psi	Internal Method
TD	42100	psi	Internal Method
Dimensional Stability			
135°C / 275°F, 7 min			
MD	-5.0	%	Internal Method
TD	-5.0	%	Internal Method
Elongation at Break			
7.9 in/min pull rate, 4.9 in jaw separation			
MD	205	%	Internal Method
TD	55	%	Internal Method
Elastic Modulus			
MD	290000	psi	Internal Method
TD	508000	psi	Internal Method
Minimum Sealing Temperature			
(Min 300g/25mm)			
Untreated			
25N/cm2 - 0,5 sec - Flat/Flat	110	°F	Internal Method
Heat Seal Range (RDM)			
RDM - 25N/cm ² - 0.5 sec - Flat/Flat			
Untreated Surface	104	°F	Internal Method
Treated - RDM - 25N/cm ² - 0.5 sec - Flat/Flat			
	95	°F	Internal Method
Coefficient of Friction			
Both Sides	0.30		Internal Method
Water Vapor Transmission Rate			
100°F, 90% RH	0.32	g/100 in ² /24 hr	Internal Method
73°F, 85% RH	0.071	g/100 in ² /24 hr	Internal Method

TYPICAL PROPERTIES : these are not to be construed as specifications

Food Contact

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: <https://www.jindalfilms.com/login-register-docmg/>

Legal Statement

This product is not intended for or supported for use in pharmaceutical or medical applications requiring compliance with EU or US Pharmacopeia.

Processing Statement

Refreshing the surface with corona treatment of the processable side before usage is recommended. Contact your Jindal Films Technical Service Representative for processing recommendations and guidelines.

Footnotes

- Please contact your Sales Representative for complete country availability

Revision date

- March 15, 2024

© 2023 Jindal Films. Jindal Films, the Jindal Films' logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. Any data included herein may be based upon: analyses of representative samples and not the actual product shipped, typical values, or otherwise. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of any non-Jindal Films' product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "Jindal Films" and "Jindal" are each used for convenience, and may include Films Americas LLC, Jindal Films Americas LLC, Films Europe S.à.r.l., Jindal Films Viron SPRL, Jindal Films India Ltd., or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, some with names including "Jindal" or "Films" and some not. Neither these terms and conditions, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.