# Bicor™ 100 LTSC

Oriented Polypropylene Film


# **Jindal**

# **Product Description**

Bicor LTSC is a two-side coated OPP film, which is designed for use in high-speed or demanding horizontal, fin seal, packaging applications. The low-temperature seal coating (LTSC) delivers a low seal initiation temperature. LTSC provides a forgiving, wide operating range for applications where accurate heat control is a problem, or dwell times vary because of frequent machine speed changes. LTSC's acrylic surface is excellent for surface printing and provides good aroma barrier.

# **Key Features**

- Wide sealing range with a low minimum seal temperature (MST)
- · Excellent seal strength and hot-tack
- Robust performance on horizontal flowpack machines
- Excellent humidity seal retention on LTSC side
- · Good flavour and aroma barrier
- · Outstanding optical properties
- Ideal support for normal ink systems



#### General

# Availability

Latin America

#### **Features**

Acrylic Coated

Humidity Resistant

# **Applications**

Biscuits/Cookie/Crackers

Tobacco

Frozen Food

#### Uses

HFFS Flexible Packaging

#### Appearance

Clear/Transparent

#### **Processing Method**

Inner Web Adhesive Lamination

Surface Print Unsupported

North America

Flavor & Aroma Barrier

Low Temperature Seal (LTS) Coated

Confectionery, Gum

Bakery

Health and Beauty Care

South America

In Lamination Lap Sealable

Very Broad Seal Range

Confectionery, Sugar

Confectionery, Chocolate

Household and Detergents

Solvent Flexographic Printing

Water-based Flexographic Printing

Solvent Rotogravure Printing

#### **Properties & Typical Values**

Property	Typical Value Unit	Test Based On
Yield	44.2 m²/kg	Internal Method
Unit Weight	22.9 g/m²	Internal Method
Film Thickness	25 μm	Internal Method
Haze	2.1 %	Internal Method
Gloss (45°)		
Acrylic Surface	90	Internal Method
Tensile Strength at Break		
510 mm/min pull rate, 50 mm jaw separation		
MD	138 Mpa	Internal Method
TD	207 Mpa	Internal Method
Dimensional Stability 135°C / 275°F, 7 min		
MD	-4.5 %	Internal Method
TD	-4.0 %	Internal Method
Crimp Seal Strength		
LTS/LTS		
127°C, 0.1 Mpa, 0.75 sec	520 g/2.5 cm	Internal Method
Crimp Seal (MST)		
LTS/LTS	71 °C	Internal Method
Coefficient of Friction	0.23	Internal Method
Water Vapor Transmission Rate		
38°C, 90% RH	5.7 g/m²/24 hr	Internal Method

TYPICAL PROPERTIES: these are not to be construed as specifications

#### **Food Contact**

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: <a href="https://www.jindalfilms.com/login-register-docmg/">https://www.jindalfilms.com/login-register-docmg/</a>

#### **Legal Statement**

This product is not intended for or supported for use in pharmaceutical or medical applications requiring compliance with EU or US Pharmacopeia.

## **Processing Statement**

- LTSC is only suitable for fin seal applications. The acrylic and LTSC coatings are not compatible for heat sealing to each other.
- Surface print and lamination characteristics are similar to other acrylic-coated films (AB, AB-X).
- Acrylic coating and its properties can be affected by humidity and water condensation. Thorough testing is recommended when considering acrylic-coated films in refrigerated or frozen applications.
- To avoid blocking, ghosting, high residual solvents, or decreased sealability, converters should eliminate the use of slow solvents (cellosolve, glycol ethers, MIBK, butanol, etc) when printing on acrylic surfaces. The use of esters should be minimized.
- The low temperature seal coated surface is not designed as the print surface. Consult ink supplier for recommendations, and conduct thorough testing prior to printing on this surface.

# **Footnotes**

- 1. Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete country availability.
- 2. Dimensional stability is reported for uncoated base film.
- 3. Tested at  $38^{\circ}$ C ( $100^{\circ}$ F)/100%RH, then calculated to 90%RH with .90 multiplier.

## **Revision date**

October 08, 2013

© 2023 Jindal Films, Jindal Films, the Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information in may be based upon: analyses of representative samples and not the actual product shipped, typical values, or otherwise. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, expressly or impliedly, the merchanish (filters), the particular purpose, freedom from patent infringement, or suitability of the products, materials or processe sections. The user is solely responsible for all determinations regarding any use of material or product and any process in the information in this document. This document is not an endorsement of any non-Jindal Films is product or process, and we expressly disclaim any contrary implication. The terms ""out," "Jindal Films Americas LLC, Films Europe Sár.I., Jindal Films Virton SPRL, Jindal Films India Ltd., or any companies affiliated with them in the production and sale of film products. There are a number of south affiliated companies, some with names including "Jindal" or "Films" and some not. Neither these terms and conditions, nor anything else in this document, is intended to override or supersed the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.