# Bicor™ 100 LTSC

**Oriented Polypropylene Film** 

# **Product Description**

Bicor LTSC is a two-side coated OPP film, which is designed for use in high-speed or demanding horizontal, fin seal, packaging applications. The low-temperature seal coating (LTSC) delivers a low seal initiation temperature. LTSC provides a forgiving, wide operating range for applications where accurate heat control is a problem, or dwell times vary because of frequent machine speed changes. LTSC's acrylic surface is excellent for surface printing and provides good aroma barrier.

# Key Features

- Wide sealing range with a low minimum seal temperature (MST)
- Excellent seal strength and hot-tack
- · Robust performance on horizontal flowpack machines
- Excellent humidity seal retention on LTSC side
- Good flavour and aroma barrier
- Outstanding optical properties
- Ideal support for normal ink systems







Jindal Films

# **Properties & Typical Values**

N/ 11		
YIEId	44.2 m²/kg	Internal Method
Unit Weight	22.9 g/m <sup>2</sup>	Internal Method
Film Thickness	25 μm	Internal Method
Haze	2.1 %	Internal Method
Gloss (45°)		
Acrylic Surface	90	Internal Method
Tensile Strength at Break		
510 mm/min pull rate, 50 mm jaw separation		
MD	138 Mpa	Internal Method
TD	207 Mpa	Internal Method
Dimensional Stability 135°C / 275°F, 7 min		
MD	-4.5 %	Internal Method
TD	-4.0 %	Internal Method
Crimp Seal Strength		
LTS/LTS		
127°C, 0.1 Mpa, 0.75 sec	520 g/2.5 cm	Internal Method
Crimp Seal (MST)		
LTS/LTS	71 °C	Internal Method
Coefficient of Friction	0.23	Internal Method
Water Vapor Transmission Rate		
38°C, 90% RH	5.7 g/m²/24 hr	Internal Method

TYPICAL PROPERTIES : these are not to be construed as specifications

## **Food Contact**

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: <u>https://www.jindalfilms.com/login-register-docmg/</u>

## Legal Statement

This product is not intended for or supported for use in pharmaceutical or medical applications requiring compliance with EU or US Pharmacopeia.

## **Processing Statement**

- LTSC is only suitable for fin seal applications. The acrylic and LTSC coatings are not compatible for heat sealing to each other.
- Surface print and lamination characteristics are similar to other acrylic-coated films (AB, AB-X).
- Acrylic coating and its properties can be affected by humidity and water condensation. Thorough testing is recommended when considering acrylic-coated films in refrigerated or frozen applications.
- To avoid blocking, ghosting, high residual solvents, or decreased sealability, converters should eliminate the use of slow solvents (cellosolve, glycol ethers, MIBK, butanol, etc) when printing on acrylic surfaces. The use of esters should be minimized.
- The low temperature seal coated surface is not designed as the print surface. Consult ink supplier for recommendations, and conduct thorough testing prior to printing on this surface.

### Footnotes

- 1. Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete country availability.
- 2. Dimensional stability is reported for uncoated base film.
- 3. Tested at 38°C (100°F)/100%RH, then calculated to 90%RH with .90 multiplier.

### **Revision date**

• October 08, 2013

© 2023 Jindal Films. Jindal Films, the Jindal Films' logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films provides prior written authorization. To the extert Jindal Films provides prior written authorization, the user may use the document or its information only if the document or its information only if the document is unaltered and complete, including all of its headers, disclaimers, disclaimers, disclaimers, and other information. Any data include herein may be based upon: analyses of representative samples and other information, nor may warrant, expressly or implicitly, the merchantability, titness for a particular purpose, freedom from patent infingement, or subability of the products, materials or products and any process, in the enterstability of rom patent infingement, or utability of the product or materials or produces and any process. In the enterstability of any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information. This document is not an endorsement of any non-indire Films' product or ompanies filtiated with them in the broduction and sale of time products. There are an unber of such affiliated companies, including "Jindal Films Americas LLC, Films Europe S and, Jindal Films Virton SPRL, Jindal Films India Lid., or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, including "Jindal Films, and some not. Neither these terms and conditions, nor any them in this document is not an endorsement of any none such affiliated companies, some with names including "Jindal Films, and some not. Neither these terms and conditions, nor anything else in this document or supersede the legal separateness of