

Ethy-Lyte™ 25HD200

Oriented Polyethylene Film




Product Description

25HD200 is a one-side treated, bi-axially oriented, high density polyethylene (BOPE) film. Designed as a high performance printing web, setting a new market standard for recyclable films.

Lamination of 25HD200 with other PE films generates fully recyclable polyethylene structures.

Due to good performance in the packaging process, 25HD200 is suitable for a broad range of applications.



Key Features

- Best performance in printing and lamination
- High mechanical stability
- Good transparency
- Consistent coefficient of friction (COF)

General

Availability

- | | | |
|------------------------|-----------------|-----------------|
| ✓ Latin America | ✓ North America | ✓ South America |
| ✓ Africa & Middle East | ✓ Asia Pacific | ✓ Europe |

Applications

- | | | |
|----------------------------|--------------------------|----------------------------|
| ✓ Biscuits/Cookie/Crackers | ✓ Bakery | ✓ Fresh Produce |
| ✓ Frozen Food | ✓ Health and Beauty Care | ✓ Household and Detergents |
| ✓ Crisps and Snacks | ✓ Pet Food | |

Uses

- | | | |
|--------------------------------|---------------------------------------|---------------------------|
| ✓ HFFS Flexible Packaging | ✓ Pre-made Bags - Flexible Packaging | ✓ VFFS Flexible Packaging |
| ✓ Pouches - Flexible Packaging | ✓ Stand Up Pouch - Flexible Packaging | |

Appearance

- ✓ Clear/Transparent

Processing Method

- | | | |
|-------------------------------------|----------------------------------|--------------------------------|
| ✓ Outer Web Adhesive Lamination | ✓ Solvent Flexographic Printing | ✓ Solvent Rotogravure Printing |
| ✓ Water-based Flexographic Printing | ✓ Outer Web Extrusion Lamination | |

Properties

Property	Typical Value	Unit	Test Based On
Yield	42.3	m ² /kg	Internal Method
Film Thickness	25	µm	Internal Method
Density	0.95	kg/dm ³	Internal Method
Gloss	85	Gloss Unit	Internal Method
Haze	5.5	%	Internal Method
Elastic Modulus			
MD	1500	Mpa	Internal Method
TD	2000	Mpa	Internal Method
Coefficient of Friction			
Untreated/Untreated	0.35		Internal Method
Treatment			
Treated Surface	40	dyne/cm	Internal Method
Water Vapor Transmission Rate			
<i>Tested at 38°C/100%RH, then calculated to 90%RH with .90 multiplier</i>			
38°C, 90% RH	5	g/m ² /24 hr	Internal Method

Food Contact

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: <https://www.jindalfilms.com/login-register-docmg/>

Legal Statement

Contact your Jindal Films Customer Service Representative for potential food contact application compliance (e.g. FDA, EU, HPFB). This product is not intended for use in medical applications and should not be used in any such applications

Processing Statement

- Contact your Jindal Films Technical Service Representative for processing recommendations and guidelines
- Refreshing of the treatment before usage recommended.

Footnotes

- Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete country availability.

Revision date

- September 02, 2021

© 2020 Jindal Films. Jindal Films, Jindal Films, the Jindal Films' logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. Any data included herein may be based upon: analyses of representative samples and not the actual product shipped, typical values, or otherwise. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of any non-Jindal Films' product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "Jindal Films" and "Jindal" are each used for convenience, and may include Films Americas LLC, Jindal Films Americas LLC, Films Europe S.à.r.l., Jindal Films Virton SPRL, Jindal Films India Ltd., or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, some with names including "Jindal" or "Films" and some not. Neither these terms and conditions, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.