Bicor™ 220AB

Oriented Polypropylene Film


Jindal

Product Description

Bicor AB is a two-side acrylic coated, sealable OPP film designed for general use in overwrap and horizontal packaging. This film is suitable as an unsupported web or in a lamination. It can be surface printed, reverse printed, or used unprinted.

Key Features

- Outstanding optical properties
- · Robust machinability
- · Low and consistent COF
- Excellent hot slip
- Excellent stiffness
- · Excellent flavor and aroma barrier
- Printable on both sides



General

Availability

Latin America

Features

Acrylic Coated

Applications

Biscuits/Cookie/Crackers

Uses

Box Overwrap Flexible Packaging

Tobacco Overwrap Flexible Packaging

Appearance

Clear/Transparent

Processing Method

Cold Seal Adhesive

Solvent Flexographic Printing

Water-based Flexographic Printing

North America

Flavor & Aroma Barrier

Box Overwrap

HFFS Flexible Packaging

Inner Web Adhesive Lamination

Solvent Rotogravure Printing

South America

In Lamination Lap Sealable

Tobacco

Pre-made Bags - Flexible Packaging

Outer Web Adhesive Lamination

Surface Print Unsupported

Properties & Typical Values

| Property | Typical Value Unit | Test Based On |
|---|--------------------|-----------------|
| Yield | 32.0 m²/kg | Internal Method |
| Unit Weight | 31.2 g/m² | Internal Method |
| Film Thickness | 34 μm | Internal Method |
| Gloss (45°) | 87 Gloss Unit | Internal Method |
| Haze | 1.9 % | Internal Method |
| Tensile Strength at Break | | |
| 510 mm/min pull rate, 50 mm jaw separation | | |
| MD | 138 Mpa | Internal Method |
| TD | 238 Mpa | Internal Method |
| Dimensional Stability 135°C / 275°F, 7 min | | |
| MD | -4.5 % | Internal Method |
| TD | -3.5 % | Internal Method |
| Crimp Seal Strength | | |
| 127°C, 0.1 Mpa, 0.75 sec | 590 g/2.5 cm | Internal Method |
| Crimp Seal (MST) | 85 °C | Internal Method |
| Coefficient of Friction | | |
| Acrylic/Acrylic | 0.22 | Internal Method |
| Water Vapor Transmission Rate | | |
| 38°C, 90% RH | 4.0 g/m²/24 hr | Internal Method |

TYPICAL PROPERTIES: these are not to be construed as specifications

Food Contact

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: https://www.jindalfilms.com/login-register-docmg/

Legal Statement

This product is not intended for or supported for use in pharmaceutical or medical applications requiring compliance with EU or US Pharmacopeia.

Processing Statement

- HS is lap sealable to other acrylic-coated and sealable PVdC-coated films.
- HS is not recommended as the sealant webs on VFFS machines because of poor hot tack.
- Acrylic coating and its properties can be affected by extreme humidity and water condensation. Thorough testing is recommended when considering acrylic-coated films in refrigerated or frozen applications.
- Acrylic coating must be primed if used in extrusion lamination.
- Acrylicrylic is an excellent surface for water-based or solvent-based inks, adhesives, and code-dating (cold wet or hot stamp) without treatment.
- To avoid blocking, ghosting, high residual solvents, or decreased sealability, converters should eliminate the use of slow solvents (cellosolve, glycol ethers, MIBK, butanol, etc) when printing on acrylic surfaces. The use of esters should be minimized.

Footnotes

- 1. Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete country availability.
- 2. Dimensional stability is reported for uncoated base film.
- 3. Tested at 38°C (100°F)/100%RH, then calculated to 90%RH with .90 multiplier.

Revision date

April 21, 2020

© 2023 Jindal Films, Jindal Films, the Jindal Films, the Jindal Films (logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footeds, and other included herein may be based upon; analyses of representatives samples and not the actual product stronged, typical values of the product or materials when not in combination with any other product or materials when not in combination with any other product or materials when not in combination with any other product or materials when not in combination with any other product or materials upon to the product of this information; nor do we warrant, expressly or impliedle, the merchantally fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials, or processed secsibled. The user is solely responsible for all determinations regarding any use of material or product and any process in the surpose of the information in this document. This document is not an endorsement of mon-Jindal Films' product or process, and we expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of mon-Jindal Films' product or process, and we expressly disclaim any contract principles of indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. The terms "we" "or," "infinial "main" are each used for convenience, and may include Films Americas