# Bicor™ AB - Oriented Polypropylene Film






#### PRODUCT DATA SHEET

# **Product Description**

Bicor AB is a two-side acrylic coated, sealable OPP film designed for general use in overwrap and horizontal packaging. This film is suitable as an unsupported web or in a lamination. It can be surface printed, reverse printed, or used unprinted.

### **Key Features**

- · Outstanding optical properties
- Robust machinability
- · Low and consistent COF
- · Excellent hot slip
- · Excellent stiffness
- · Excellent flavor and aroma barrier
- Printable on both sides



# **Properties & Typical Values**

Properties	Unit	220AB	310AB	380AB	Test Method
Yield	in²/lb	22500	31000	38000	ITM 01
Unit Weight	lb/ream	19.2	13.9	11.4	ITM 01
Film Thickness	mil	1.3	1.0	0.80	ITM 02
Gloss (45°)	Gloss Units	87	87	90	ITM 14
Haze	%	1.9	1.7	1.6	ITM 06
Tensile Strength at Break - MD TD 20 in/min pull rate, 2.0 in jaw separation	psi	20000 34500	19900 34200	20000 33000	ITM 50
Dimensional Stability 135°C / 275°F, 7 min - MD TD	%	-4.5 -3.5	-4.5 -3.5	-4.5 -4.0	ITM 37
Seal Strength (RDM) - 260°F, 20 psi, 0.75 sec	g/in	600	560	540	ITM26
Crimp Seal (MST)	°F	185	205	185	
Coefficient of Friction - Acrylic/Acrylic		0.22	0.24	0.25	ITM 20
Water Vapor Transmission Rate - 100°F, 90% RH	g/100 in²/24 hr	0.26	0.37	0.47	ITM 46

## TYPICAL VALUES SHOULD NOT BE CONSTRUED AS FINISHED PRODUCT SPECIFICATIONS (FPS).

# **Market Segments**

✓ Biscuits/Cookie/Crackers  Applications	<b>✓</b> Box Overwrap	✓ Tobacco
<ul><li>Box Overwrap Flexible Packaging</li><li>Tobacco Overwrap Flexible Packaging</li></ul>	✓ HFFS Flexible Packaging	✔ Pre-made Bags - Flexible Packaging
Processing Method		
✓ Cold Seal Adhesive	✓ Inner Web Adhesive Lamination	✓ Outer Web Adhesive Lamination
✓ Solvent Flexographic Printing	Solvent Rotogravure Printing	✓ Surface Print Unsupported

## **Food Contact**

✓ Water-based Flexographic Printing

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: <a href="http://www.jindalfilms.com/login-register-docmg/">http://www.jindalfilms.com/login-register-docmg/</a>

# **Legal Statement**

This product is not intended for or supported for use in pharmaceutical or medical applications requiring compliance with EU or US Pharmacopeia.

#### **Processing Statement**

- HS is lap sealable to other acrylic-coated and sealable PVdC-coated films.
- HS is not recommended as the sealant webs on VFFS machines because of poor hot tack.
- Acrylic coating and its properties can be affected by extreme humidity and water condensation. Thorough testing is recommended when considering acrylic-coated films in refrigerated or frozen applications.
- Acrylic coating must be primed if used in extrusion lamination.
- Acrylicrylic is an excellent surface for water-based or solvent-based inks, adhesives, and code-dating (cold wet or hot stamp) without treatment.
- To avoid blocking, ghosting, high residual solvents, or decreased sealability, converters should eliminate the use of slow solvents (cellosolve, glycol ethers, MIBK, butanol, etc) when printing on acrylic surfaces. The use of esters should be minimized.

#### **Storage**

You will find all information about storage conditions into the sign in area of our websitehttp://www.jindalfilms.com/login-registerdocmg/, under the section "Information on food safety and quality practices". The name of the document is "Storage recommendations".

#### **Footnotes**

- 1. Product may not be available in one or more countries in the identfied Availability regions. Please contact your Sales Representative for complete country availability
- 2. Dimensional stability is reported for uncoated base film.
- 3. Tested at 38°C (100°F)/100%RH, then calculated to 90%RH with .90 multiplier.

Revision date: April 21, 2020

© 2024 Jindal Films, Jindal Films, the Jindal Films the Jindal Films togo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, times for a particular purpose, freedom from part infinigement, or suitability of the products, materials or processes described. The user into the expressly decided in lability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone the complete of the products of the product of the products of the products of the products of the product of the product