


OPPalyte™ 278 WOS-2

Oriented Polypropylene Film



Product Description

OPPalyte WOS-2 is a one-side treated, one-side sealable, white opaque OPP film with a proprietary cavitated core. WOS-2 was developed to provide performance improvements over 278 WOS in terms of lower and more consistent COF, lower MST, and improved print performance. WOS-2 was developed and designed for frozen novelty applications. The stiffness, slip characteristics, and sealability of WOS-2 have been optimized to provide outstanding performance on multi-lane equipment.



Key Features

- Outstanding opacity
- Robust machinability
- Heat seal range of approximately 115°F (63°C)
- Average seal strengths over 480 g/in (480 g/2.5 cm)
- Bright white appearance

General

Availability

- ✓ Latin America
- ✓ North America
- ✓ South America

Features

- ✓ In Lamination Lap Sealable
- ✓ Light Barrier

Applications

- ✓ Biscuits/Cookie/Crackers
- ✓ Bakery
- ✓ Dairy Products
- ✓ Ice Cream

Uses

- ✓ HFFS Flexible Packaging
- ✓ Pre-made Bags - Flexible Packaging
- ✓ VFFS Flexible Packaging

Appearance

- ✓ White

Processing Method

- ✓ Inner Web Adhesive Lamination
- ✓ Solvent Flexographic Printing
- ✓ Solvent Rotogravure Printing
- ✓ Surface Print Unsupported
- ✓ Water-based Flexographic Printing
- ✓ Inner Web Extrusion Lamination

Properties & Typical Values

Property	Typical Value	Unit	Test Based On
Yield	27800	in ² /lb	Internal Method
Unit Weight	15.5	lb/ream	Internal Method
Film Thickness	1.7	mil	Internal Method
Gloss (45°)			
Treated Surface	70		Internal Method
Opacity	85	%	Internal Method
Light Transmission	24.0	%	Internal Method
Tensile Strength at Break			
20 in/min pull rate, 2.0 in jaw separation			
MD	11400	psi	Internal Method
TD	17800	psi	Internal Method
Dimensional Stability			
135°C / 275°F, 7 min			
MD	-4.5	%	Internal Method
TD	-4.0	%	Internal Method
Crimp Seal Strength			
Untreated/Untreated			
210°F, 20 psi, 0.75 sec	480	g/in	Internal Method
Crimp Seal (MST)			
Untreated/Untreated	186	°F	Internal Method
Coefficient of Friction			
Treated/Treated	0.36		Internal Method
Wettability			
Treated Surface	0.80	receding cos θ	Internal Method
Water Vapor Transmission Rate			
100°F, 90% RH	0.31	g/100 in ² /24 hr	Internal Method

TYPICAL PROPERTIES : these are not to be construed as specifications

Food Contact

Any further regulatory information on this product (i.e. Food Contact application, Presence/absence of substances, Reach, ...) are accessible on the below link: <https://www.jindalfilms.com/login-register-docmg/>

Legal Statement

This product is not intended for or supported for use in pharmaceutical or medical applications requiring compliance with EU or US Pharmacopeia.

Processing Statement

- WOS-2 contains a non-migratory slip package for excellent machinability and hot slip without compromising appearance or seals. Do not retreat.
- WOS-2 should be primed for extrusion laminations or when laminating with high-barrier PVdC to ensure consistent adhesion.
- WOS-2 may need to be primed when surface printing with water-based inks.
- WOS-2 is lap sealable to coextruded films.

Footnotes

1. Product may not be available in one or more countries in the identified Availability regions. Please contact your Sales Representative for complete country availability.
2. Tested at 38°C (100°F)/100%RH, then calculated to 90%RH with .90 multiplier.

Revision date

- November 22, 2023

© 2023 Jindal Films. Jindal Films, the Jindal Films' logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. Any data included herein may be based upon: analyses of representative samples and not the actual product shipped, typical values, or otherwise. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of any non-Jindal Films' product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "Jindal Films" and "Jindal" are each used for convenience, and may include Films Americas LLC, Jindal Films Americas LLC, Films Europe S.à.r.l., Jindal Films Virton SPRL, Jindal Films India Ltd., or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, some with names including "Jindal" or "Films" and some not. Neither these terms and conditions, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.