

OPPalyte™ white opaque uncoated films at a glance

Flexible packaging range

OPPalyte™
films

OPP film type	STRUCTURE						KEY PROPERTIES							MAIN PACKAGING FORMATS			MAIN USE		KEY MARKETS			
	Thickness ^x (µm)	Yield (m ² /kg)	Unit Weight (g/m ²)	Density (g/cm ³)	Side 1	Side 2	Gloss 20°	Gloss 45°	Light Transmission %	H ₂ O Permeability WVTR at 38 °C/80% RH (g/m ² /day)	Heat Seal Range (°C)	COF (in)	COF (out)	HFFS	VFFS	Overwrapping	Single Web or Laminate	Heat Seal or Cold Seal	Biscuit & Bakery	Confectionary Chocolate	Ice cream	Snacks, Nuts, Cereals
Heat Seal and Cold Seal																						
D0447	38	48,8	20,5	0,54	Treated	Heat Sealable layer	-	70	21,0	-	45*	0,35	-	v	-	v	Single web	Heat Seal	v	v	v	v
ICE	33	48,8	20,5	0,62	Treated	Heat Sealable layer	-	75	24,0	-	45*	-	-	v	-	-	Single web	Cold Seal	-	-	v	-
	38	42,4	23,6	0,62	Treated	Heat Sealable layer	-	90	21,0	-	45*	-	-	v	-	-	Single web	Cold Seal	-	-	v	-
HGP	34	40,8	24,5	0,72	Treated	Heat Sealable layer	9	-	-	7,6	30**	0,25	-	v	v	-	Single web	Heat Seal	v	v	-	-
	40	34,7	28,8	0,72	Treated	Heat Sealable layer	9	-	-	6,5	30**	0,25	-	v	v	-	Single web	Heat Seal	v	v	-	-
MD447	30	41,6	24,0	0,80	Treated	Heat Sealable layer	-	55	35,0	5,0	45 (Seal) / 35 (Treated)*	0,25	0,30	v	v	v	Both	Heat Seal	v	v	v	v
	35	35,8	27,9	0,80	Treated	Heat Sealable layer	-	55	33,0	4,5	45 (Seal) / 35 (Treated)*	0,25	0,30	v	v	v	Both	Heat Seal	v	v	v	v
	40	31,3	31,9	0,80	Treated	Heat Sealable layer	-	55	30,0	4,0	45 (Seal) / 35 (Treated)*	0,25	0,30	v	v	v	Single web	Heat Seal	v	v	v	v
WTD	20	52,1	19,2	0,96	Treated	Heat Sealable layer	52	-	-	8,3	65*	0,35	0,47	v	v	v	Both	Heat Seal	v	v	v	v
	25	41,7	24,0	0,96	Treated	Heat Sealable layer	52	-	-	6,6	65*	0,35	0,47	v	v	v	Both	Heat Seal	v	v	v	v
	30	34,7	28,8	0,96	Treated	Heat Sealable layer	52	-	-	5,5	65*	0,35	0,47	v	v	v	Both	Heat Seal	v	v	v	v
	35	29,8	33,6	0,96	Treated	Heat Sealable layer	52	-	-	4,7	65*	0,35	0,47	v	v	v	Both	Heat Seal	v	v	v	v
	40	26,0	38,4	0,96	Treated	Heat Sealable layer	52	-	-	4,1	65*	0,35	0,47	v	v	v	Single web	Heat Seal	v	v	v	v
Heat Seal																						
VLD	40	42,6	23,5	0,62	Treated	Peelable Layer	60	-	-	5,5	60**	0,25	-	v	-	-	Both	Heat Seal	v	v	v	-
STD	28	46,5	21,5	0,75	Treated	VBSR	65	-	-	5,5	60**	0,30	-	v	-	-	Both	Heat Seal	v	v	v	-
	35	38,5	26,0	0,75	Treated	VBSR	65	-	-	4,5	60**	0,30	-	v	-	-	Both	Heat Seal	v	v	v	-
	40	33,3	30,0	0,75	Treated	VBSR	65	-	-	4,0	60**	0,30	-	v	-	-	Both	Heat Seal	v	v	v	-
	50	27,0	37,0	0,75	Treated	VBSR	65	-	-	3,0	60**	0,30	-	v	-	-	Both	Heat Seal	v	v	v	-
	28	47,6	21,0	0,75	Treated	Heat Sealable layer	50	-	-	4,8	40**	0,30	-	v	v	-	Laminate	Heat Seal	v	v	-	v

^x Thickness is a general product reference and may or may not be the actual finished thickness of the product (see product data sheet)

√ = Typical recommended use - = Not applicable or not specified

VBSR = Very Broad Sealing Range

* Temperature range to achieve 300 g/25mm seal force when sealed with flat jaws at 25 N/cm² pressure and 0,5 s dwell time

** Temperature range to achieve 1,0 N/15mm seal force when sealed with flat jaws at 10 N/cm² pressure and 0,5 s dwell time

OPPalyte™ white opaque uncoated films at a glance

Flexible packaging range

OPPalyte™
films

OPP film type	STRUCTURE					KEY PROPERTIES								MAIN PACKAGING FORMATS			MAIN USE		KEY MARKETS			
	Thickness ^x (µm)	Yield (m ² /kg)	Unit Weight (g/m ²)	Density (g/cm ³)	Side 1	Side 2	Gloss 20°	Gloss 45°	Light Transmission %	H ₂ O Permeability WVTR at 38 °C/90% RH (g/m ² /day)	Heat Seal Range (°C)	COF (in)	COF (out)	HFSS	VFFS	Overwrapping	Single Web or Laminate	Heat Seal or Cold Seal	Biscuit & Bakery	Confectionary Chocolate	Ice cream	Snacks, Nuts, Cereals
Cold Seal																						
MW247	33	48,8	20,5	0,62	Treated	Cold Seal Receptive layer	-	75	22,0	6,1	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	38	42,4	23,6	0,62	Treated	Cold Seal Receptive layer	-	75	21,0	5,2	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	47	34,4	29,0	0,62	Treated	Cold Seal Receptive layer	-	75	16,0	4,1	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
MH247	35	39,4	25,4	0,73	Treated	Cold Seal Receptive layer	-	70	32,0	4,9	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	40	34,4	29,0	0,73	Treated	Cold Seal Receptive layer	-	70	25,0	4,2	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
	50	27,5	36,3	0,73	Treated	Cold Seal Receptive layer	-	70	22,0	3,0	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
SHD	28	46,5	21,5	0,75	Treated	Cold Seal Receptive layer	70	-	-	5,5	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	35	38,5	26,0	0,75	Treated	Cold Seal Receptive layer	70	-	-	4,5	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	40	33,3	30,0	0,75	Treated	Cold Seal Receptive layer	70	-	-	4,0	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
	50	27,0	37,0	0,75	Treated	Cold Seal Receptive layer	70	-	-	3,0	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
	60	22,2	45,0	0,75	Treated	Cold Seal Receptive layer	70	-	-	2,5	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
SHH	28	46,5	21,5	0,75	Treated	Treated	70	-	-	5,5	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	40	33,3	30,0	0,75	Treated	Treated	70	-	-	4,0	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
ORH	60	30,3	33,0	0,55	Treated	Treated	33	-	-	-	-	-	-	v	v	-	Single web	Cold Seal	v	v	v	-
	70	26,0	38,5	0,55	Treated	Treated	33	-	-	-	-	-	-	v	v	-	Single web	Cold Seal	v	v	v	-

^x Thickness is a general product reference and may or may not be the actual finished thickness of the product (see product data sheet)

√ = Typical recommended use - = Not applicable or not specified

VBSR = Very Broad Sealing Range

* Temperature range to achieve 300 g/25mm seal force when sealed with flat jaws at 25 N/cm² pressure and 0,5 s dwell time

** Temperature range to achieve 1,0 N/15mm seal force when sealed with flat jaws at 10 N/cm² pressure and 0,5 s dwell time

May 2023

Contact your Jindal Films representative for more information

www.jindalfilms.com

info@jindalfilms.com

Jindal
Films

© 2023 Jindal Films. Jindal Films, the Jindal Films' logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. Any data included herein may be based upon: analyses of representative samples and not the actual product shipped, typical values, or otherwise. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of any non-Jindal Films' product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "Jindal Films" and "Jindal" are each used for convenience, and may include Films Americas LLC, Jindal Films Americas LLC, Films Europe S.à.r.l., Jindal Films Virton SPRL, Jindal Films India Ltd., or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, some with names including "Jindal" or "Films" and some not. Neither these terms and conditions, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.