



RECYCLABLE PP MONO-MATERIAL SOLUTION WITH HIGH SEAL PERFORMANCE OPP films

PP-based high performance barrier laminate for high speed HFFS machines

MONO-MATERIAL SOLUTION

PRINT WEB: BICOR 12MB100 – heat stable

OPP film

INNER WEB: METALLYTE 20MLB – Clear high

barrier metallized OPP film with

broad seal range

CONVERSION: SIT Group SIT



PACKAGING MACHINERY

SUPPLIER: IMA GROUP

EUROSICMA

FORMAT: HFFS flow-wrap

TYPE: EURO 88 EDG

EURO 88 EDG IN LINE



Features

- Mono-material compositions (>90% PP)
- Thin heat resistant OPP with high Modulus and low shrinkage to enable rotogravure printing
- Very low heat seal initiation temperature met-OPP for very broad seal operating range (VBSR)
- Great balance of properties with heat resistance of thin outer web and very low SIT of inner web
- Ideal for most single-portion packs

Benefits

- Conforms to CEFLEX recycling guidelines
- Full compatibility for mechanical recycling in PP or mixed PO streams
- PET-free and Paper-Free solutions
- Great barrier keeps dry products with first day freshness
- Robust HFFS performance for demanding high speed flow-wrap applications
- Provides great protection for sensitive biscuits, baked goods or confectioneries
- Delivers packaging weight reduction compared to most PET based laminates.









BICOR™ MB100 is a very thin transparent non heat sealable OPP film with improved heat stability (low shrinkage) and very high Modulus for optimal machinability during conversion (e.g. rotogravure print) and on VFFS machines

Metallyte™ MLB is a transparent high barrier vacuum metallized film with great moisture barrier (WVTR 0.3) and medium oxygen barrier (OTR 40) with excellent low temperature seal initiation temperature (SIT) designed for HFFS

12MB100/20MLB laminate is an ideal 2-ply OPP based barrier solution for flow-wrap customers requiring a recyclable PP mono-material design that was previously in non-recyclable constructions (e.g. PET/Met-OPP or Paper/Met-OPP) running at high linear speeds.

Demanding high speed HFFS formats usually resort to 2-ply non-mechanically recyclable laminates such as PET/Met-OPP. They can now be replaced with PP-based laminates using higher performance OPP films to deliver improved recyclability and conform to CEFLEX design guidelines in Europe.

HFFS 2-PLY LAMINATES FOR BAKERY & CONFECTIONERY SEGMENTS	MECHANICALLY RECYCLABIF	UNIT WEIGHT (g/m²)	"WVTR 38°C, 90%RH"	"OTR 23°C, 0%RH"	HFFS SEAL PERFORMANCE
15OPP / 20Met-OPP	~	100%	0,3	50	++
12MB100 / 20MLB	~	92%	0,3	40	+++
10PET / 20Met-OPP	х	101%	0,3	50	++++
12PET / 20Met-OPP	X	98%	0,3	50	++++

Jindal Films data

For use in market segments typically using PET based laminates on HFFS machines with heat sealed flow-packs:

- Various biscuits, cookies or crackers
- Baked goods
- Sweet confectioneries
- Home& Personal Care products for portion packs such as detergent tablets
- Potentially any application where high speed is required



Contact your Jindal Films representative for more information

www.jindalfilms.com

info@jindalfilms.com





© 2023 Jindal Films. Jindal Films, Jindal Films, Ho Jindal Films' logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or is information, whether in whole or in part, whether in whold Jindal Films, prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. Any data included herein may be based upon: analyses of representative samples and not the actual product or materials were the information in this document in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim any contrary implication. The terms "we"," or", "inidal Films" and "sindal" and "sindal" or convenience, and may include Films Americas LLC, Jindal Films Europe S.Aff., Jindal Films and some not. Neither these terms and conditions, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.