

JINDAL FILMS BOPP FILMS WITH IMPROVED SEAL PERFORMANCE

MATERIAL REPLACEMENT	HEAT SEAL PERFORMANCE	OPP FILM	BASE FILM ASPECT	SIT (°C)	SEAL STRENGTH	WVTR 38°C; 90%RH	OTR 23°C; 0%RH
STANDARD OPP APPLICATIONS	BROAD SEAL RANGE (LOW SIT)	HLD	Clear	80	+	**	
		STD	White	80	+	**	
		SVD	White	100	Peelable	**	
		MLB	Metallized	85	++	0	40
		MM398	Metallized	85	++	0.3	50
		QFM	White/Metallized	85	+	0.2	30
EXTRUSION COATED PE	ENHANCED SEAL	UBWES	White/Metallized	80	+++	0.1	0.1
PE & CPP	ULTRA SEAL	MB344US	Clear	95	++++	**	**