

# OPPalyte™ white opaque uncoated films at a glance

## Flexible packaging range

OPPalyte™  
films

OPP film type	STRUCTURE						KEY PROPERTIES							MAIN PACKAGING FORMATS			MAIN USE		KEY MARKETS			
	Thickness <sup>x</sup> (µm)	Yield (m <sup>2</sup> /kg)	Unit Weight (g/m <sup>2</sup> )	Density (g/cm <sup>3</sup> )	Side 1	Side 2	Gloss 20°	Gloss 45°	Light Transmission %	H <sub>2</sub> O Permeability WVTR at 38 °C/80% RH (g/(m <sup>2</sup> /day))	Heat Seal Range (°C)	COF (in)	COF (out)	HFFS	VFFS	Overwrapping	Single Web or Laminate	Heat Seal or Cold Seal	Biscuit & Bakery	Confectionary Chocolate	Ice cream	Snacks, Nuts, Cereals
<b>Heat Seal and Cold Seal</b>																						
<b>D0447</b>	38	48,8	20,5	0,54	Treated	Heat Sealable layer	-	70	21,0	5,4	45*	0,35	-	v	-	v	Single web	Heat Seal	v	v	v	v
<b>ICE</b>	33	48,8	20,5	0,62	Treated	Heat Sealable layer	-	75	24,0	5,9	45*	-	-	v	-	-	Single web	Cold Seal	-	-	v	-
	38	42,4	23,6	0,62	Treated	Heat Sealable layer	-	90	21,0	5,0	45*	-	-	v	-	-	Single web	Cold Seal	-	-	v	-
<b>HGP</b>	40	34,7	28,8	0,72	Treated	BSR	9	-	-	6,5	30**	0,25	-	v	v	-	Single web	Heat Seal	v	v	-	-
<b>MD447</b>	30	41,6	24,0	0,80	Treated	BSR	40	55	33,0	5,0	45 (Seal) / 35 (Treated)*	0,25	0,30	v	v	v	Both	Heat Seal	v	v	v	v
	35	35,8	27,9	0,80	Treated	BSR	40	55	29,0	4,5	45 (Seal) / 35 (Treated)*	0,25	0,30	v	v	v	Both	Heat Seal	v	v	v	v
<b>WTD</b>	20	52,1	19,2	0,96	Treated	BSR	52	-	-	8,3	65*	0,35	0,47	v	v	v	Both	Heat Seal	v	v	v	v
	25	41,7	24,0	0,96	Treated	BSR	52	-	-	6,6	65*	0,35	0,47	v	v	v	Both	Heat Seal	v	v	v	v
	30	34,7	28,8	0,96	Treated	BSR	52	-	-	5,5	65*	0,35	0,47	v	v	v	Both	Heat Seal	v	v	v	v
	35	29,8	33,6	0,96	Treated	BSR	52	-	-	4,7	65*	0,35	0,47	v	v	v	Both	Heat Seal	v	v	v	v
	40	26,0	38,4	0,96	Treated	BSR	52	-	-	4,1	65*	0,35	0,47	v	v	v	Single web	Heat Seal	v	v	v	v
<b>Heat Seal</b>																						
<b>STD</b>	28	46,5	21,5	0,75	Treated	VBSR	65	-	-	5,5	60**	0,30	-	v	-	-	Both	Heat Seal	v	v	v	-
	35	38,5	26,0	0,75	Treated	VBSR	65	-	-	4,5	60**	0,30	-	v	-	-	Single web	Heat Seal	v	v	v	-
	40	33,3	30,0	0,75	Treated	VBSR	65	-	-	4,0	60**	0,30	-	v	-	-	Single web	Heat Seal	v	v	v	-
	50	27,0	37,0	0,75	Treated	VBSR	65	-	-	3,0	60**	0,30	-	v	-	-	Single web	Heat Seal	v	v	v	-
<b>SVD</b>	28	47,6	21,0	0,75	Treated	Heat Sealable layer	50	-	-	4,8	40**	0,30	-	v	v	-	Laminate	Heat Seal	v	v	-	v

<sup>x</sup> Thickness is a general product reference and may or may not be the actual finished thickness of the product (see product data sheet)

√ = Typical recommended use    - = Not applicable or not specified

VBSR = Very Broad Sealing Range

\* Temperature range to achieve 300 g/25mm seal force when sealed with flat jaws at 25 N/cm<sup>2</sup> pressure and 0,5 s dwell time

\*\* Temperature range to achieve 1,0 N/15mm seal force when sealed with flat jaws at 10 N/cm<sup>2</sup> pressure and 0,5 s dwell time

September 2025

**Jindal**  
Films

# OPPalyte™ white opaque uncoated films at a glance

## Flexible packaging range

OPPalyte™  
films

OPP film type	STRUCTURE						KEY PROPERTIES							MAIN PACKAGING FORMATS			MAIN USE		KEY MARKETS			
	Thickness <sup>x</sup> (µm)	Yield (m <sup>2</sup> /kg)	Unit Weight (g/m <sup>2</sup> )	Density (g/cm <sup>3</sup> )	Side 1	Side 2	Gloss 20°	Gloss 45°	Light Transmission %	H <sub>2</sub> O Permeability WVTR at 38 °C/90% RH (g/m <sup>2</sup> /day)	Heat Seal Range (°C)	COF (in)	COF (out)	HFFS	VFFS	Overwrapping	Single Web or Laminate	Heat Seal or Cold Seal	Biscuit & Bakery	Confectionary Chocolate	Ice cream	Snacks, Nuts, Cereals
<b>Cold Seal</b>																						
<b>MW247</b>	33	48,8	20,5	0,62	Treated	Cold Seal Receptive layer	-	75	22,0	6,1	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	38	42,4	23,6	0,62	Treated	Cold Seal Receptive layer	-	75	21,0	5,2	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	47	34,4	29,1	0,62	Treated	Cold Seal Receptive layer	-	75	16,0	4,1	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
<b>MH247</b>	35	39,4	25,4	0,73	Treated	Cold Seal Receptive layer	-	70	32,0	4,9	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	40	34,4	29,0	0,73	Treated	Cold Seal Receptive layer	-	70	25,0	4,2	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
	50	27,5	36,3	0,73	Treated	Cold Seal Receptive layer	-	70	22,0	3,0	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
<b>SHD</b>	28	46,5	21,5	0,75	Treated	Cold Seal Receptive layer	70	-	-	5,5	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	35	38,5	26,0	0,75	Treated	Cold Seal Receptive layer	70	-	-	4,5	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
	40	33,3	30,0	0,75	Treated	Cold Seal Receptive layer	70	-	-	4,0	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
	50	27,0	37,0	0,75	Treated	Cold Seal Receptive layer	70	-	-	3,0	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
	60	22,2	45,0	0,75	Treated	Cold Seal Receptive layer	70	-	-	2,5	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-
<b>SHH</b>	28	46,5	21,5	0,75	Treated	Treated	70	-	-	5,5	-	-	-	v	-	-	Both	Cold Seal	v	v	v	-
	40	33,3	30,0	0,75	Treated	Treated	70	-	-	4,0	-	-	-	v	-	-	Single web	Cold Seal	v	v	v	-

<sup>x</sup> Thickness is a general product reference and may or may not be the actual finished thickness of the product (see product data sheet)

√ = Typical recommended use - = Not applicable or not specified

VBSR = Very Broad Sealing Range

\* Temperature range to achieve 300 g/25mm seal force when sealed with flat jaws at 25 N/cm<sup>2</sup> pressure and 0,5 s dwell time

\*\* Temperature range to achieve 1,0 N/15mm seal force when sealed with flat jaws at 10 N/cm<sup>2</sup> pressure and 0,5 s dwell time

September 2025

Contact your Jindal Films representative for more information

[www.jindalfilms.com](http://www.jindalfilms.com)

[info@jindalfilms.com](mailto:info@jindalfilms.com)

**Jindal**  
Films

© 2025 Jindal Films. Jindal Films, the Jindal Films' logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. Any data included herein may be based upon: analyses of representative samples and not the actual product shipped, typical values, or otherwise. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of any non-Jindal Films' product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "Jindal Films" and "Jindal" are each used for convenience, and may include Films Americas LLC, Jindal Films Americas LLC, Films Europe S.à.r.l., Jindal Films Virton SPRL, Jindal Films India Ltd., or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, some with names including "Jindal" or "Films" and some not. Neither these terms and conditions, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.