

Metallized films at a glance

Flexible packaging range

Metallyte™
films

OPP FILM TYPE	STRUCTURE				KEY PROPERTIES								MAIN PACKAGING FORMATS			KEY MARKETS				
	Thickness* (µm)	Clear / White	Metal side	Non Metal side	Unit Weight (g / m²)	Yield (m² / kg)	Aroma Barrier	WVTr (g / m² / day)	OTR (cc/m²/day)	Optical Density	Heat Seal Range (°C)	COF	HFFS	VFFS	Single Web	Biscuit & Bakery	Confectionery	Snacks, Nuts, Cereals	HBA, HPC, Pet food	Dry food and Beverage powders
Ultra high barrier																				
MM883	16	Clear	Metal	Treated	14,1	70,9	v	0,1	0,1	2,8	-	-	v	v	-	v	v	v	v	v
MML883	18	Clear	Metal	Treated	16,4	61	v	0,1	0,1	2,8	-	-	v	v	-	-	-	-	v	v
MU842	28	White	Metal	Treated	20,7	49,4	v	0,1	0,1	2,5	-	-	v	v	v	v	v	v	v	v
	35	White	Metal	Treated	25,2	39,7	v	0,1	0,1	2,5	-	-	v	v	v	v	v	v	v	v
UBWES	28	White	Metal	Enhanced seal	20,7	48,4	v	0,1	0,1	3,0	79*	-	v	v	-	v	v	v	v	v
High Barrier																				
MM388	15	Clear	Metal	VBSR	13,7	73,3	-	0,3	50	2,3	65*	0,55	v	-	-	v	v	v	v	-
MLB	20	Clear	Metal	VBSR	18,2	54,9	-	0,3	40	2,2	84*	0,40	v	-	-	v	v	v	v	-
	30	Clear	Metal	VBSR	27,3	36,6	-	0,3	40	2,2	84*	0,40	v	-	-	v	v	v	v	-
MM388	18	Clear	Metal	BSR	16,4	61,1	-	0,2	26	2,5	40*	-	v	v	v	v	v	v	v	-
MM488	12	Clear	Metal	BSR	10,9	91,6	-	0,3	50	2,3	40*	0,32	v	v	-	v	v	v	v	-
	15	Clear	Metal	BSR	13,7	73,3	-	0,3	50	2,3	40*	0,32	v	v	-	v	v	v	v	-
	18	Clear	Metal	BSR	16,4	61,1	-	0,3	50	2,3	40*	0,40	v	v	v	v	v	v	v	-
MM288	15	Clear	Metal	Treated	13,7	73,2	-	0,1	25	2,8	-	-	v	v	-	v	v	v	v	v
QFM	35	White	Metal	VBSR	23,5	42,6	-	0,2	30	3,0	55**	-	v	-	-	v	v	-	-	-
Decorative / Low barrier																				
MM480	15	Clear	Metal	Standard Sealing Range	13,7	73,3	-	0,6	-	2,1	40*	-	v	v	-	v	v	v	v	-
	18	Clear	Metal	Standard Sealing Range	16,4	61,1	-	0,6	-	2,1	40*	-	v	v	-	v	v	v	v	-
	20	Clear	Metal	Standard Sealing Range	18,2	54,9	-	0,6	-	2,1	40*	-	v	v	-	v	v	v	v	-
	30	Clear	Metal	Standard Sealing Range	26,4	37,9	-	0,6	-	2,1	40*	-	v	v	-	v	v	v	v	-
MW480	38	White	Metal	Standard Sealing Range	23,6	42,4	-	0,5	80	2,3	45*	0,40	v	v	-	v	v	v	v	-
MW280	38	White	Metal	Cold Seal Receptive Layer	23,6	42,4	-	2,5	-	2,3	-	-	v	-	v	v	v	-	v	-
MH0280	35	White	Metal	Treated	25,4	39,4	-	1,5	-	2,3	-	-	v	-	-	v	v	-	-	-
ICE M	38	White	Metal	Standard Sealing Range	23,6	42,4	-	-	-	2,1	45*	-	v	-	-	-	-	-	-	-

V = typical or recommended use

- = not applicable or not specified

*Thickness is a general product reference and may or may not be the actual finished thickness of the product; see product data sheet.

BSR = Broad Sealing Range

VBSR = Very Broad Sealing Range

*Temperature range to achieve 300 g/25mm seal force when sealed with flat jaws at 25 N/cm² pressure and 0,5 s dwell time

**Temperature range to achieve 1,0 N/15mm seal force when sealed with flat jaws at 10 N/cm² pressure and 0,5 s dwell time

September 2025

Metallized films at a glance

Flexible packaging range

Metallyte™
films

OPP FILM TYPE	STRUCTURE			KEY PROPERTIES								MAIN PACKAGING FORMATS			KEY MARKETS				
	Thickness* (µm)	Metal side	Non Metal side	Unit weight (g / m²)	Yield (m² / kg)	Aroma Barrier	WVTr (g / m² / day)	OTR (cc/m²/day)	Optical Density	Heat Seal Range (°C)	COF	HFFS	VFFS	Single Web	Biscuit & Bakery	Confectionery	Snacks, Nuts, Cereals	HBA, HPC, Pet food	Dry food and Beverage powders
CLEAR films																			
MM480	15	Metal	Standard Sealing Range	13,7	73,3	-	0,6	-	2,1	40*	-	v	v	-	v	v	v	v	-
	18	Metal	Standard Sealing Range	16,4	61,1	-	0,6	-	2,1	40*	-	v	v	-	v	v	v	v	-
	20	Metal	Standard Sealing Range	18,2	54,9	-	0,6	-	2,1	40*	-	v	v	-	v	v	v	v	-
	30	Metal	Standard Sealing Range	26,4	37,9	-	0,6	-	2,1	40*	-	v	v	-	v	v	v	v	-
MM488	12	Metal	BSR	10,9	91,6	-	0,3	50	2,3	40*	0,32	v	v	-	v	v	v	-	-
	15	Metal	BSR	13,7	73,3	-	0,3	50	2,3	40*	0,32	v	v	-	v	v	v	v	-
	18	Metal	BSR	16,4	61,1	-	0,3	50	2,3	40*	0,40	v	v	v	v	v	v	v	-
MM388	18	Metal	BSR	16,4	61,1	-	0,2	26	2,5	40*	-	v	v	-	-	-	-	v	v
MM398	15	Metal	VBSR	13,7	73,3	-	0,3	50	2,3	65*	0,55	v	-	-	v	v	v	v	-
MLB	20	Metal	VBSR	18,2	54,9	-	0,3	40	2,2	84*	0,40	v	-	-	v	v	v	v	-
	30	Metal	VBSR	27,3	36,6	-	0,3	40	2,2	84*	0,40	v	-	-	v	v	v	v	-
MM288	15	Metal	Treated	13,7	73,2	-	0,1	25	2,8	-	-	v	v	-	v	v	v	v	v
MM883	16	Metal	Treated	14,1	70,9	v	0,1	0,1	2,8	-	-	v	v	-	v	v	v	v	v
MML883	18	Metal	Treated	16,4	61	v	0,1	0,1	2,8	-	-	v	v	-	-	-	-	v	v
WHITE films																			
ICE M	38	Metal	Standard Sealing Range	23,6	42,4	-	-	-	2,1	45*	-	v	-	-	-	-	-	-	-
MW280	38	Metal	Cold Seal Receptive Layer	23,6	42,4	-	2,5	-	2,3	-	-	v	-	v	v	v	-	v	-
MW480	38	Metal	Standard Sealing Range	23,6	42,4	-	0,5	80	2,3	45*	0,40	v	v	-	v	v	v	v	-
QFM	35	Metal	VBSR	23,5	42,6	-	0,2	30	3,0	55**	-	v	-	-	v	v	-	-	-
UBWES	28	Metal	Enhanced seal	20,7	48,4	v	0,1	0,1	3,0	79*	-	v	v	-	v	v	v	v	v
MU842	28	Metal	Treated	20,7	49,4	v	0,1	0,1	2,5	-	-	v	v	v	v	v	v	v	v
	35	Metal	Treated	25,2	39,7	v	0,1	0,1	2,5	-	-	v	v	v	v	v	v	v	v
MH0280	35	Metal	Treated	25,4	39,4	-	1,5	-	2,3	-	-	v	-	-	v	v	-	-	-

V = typical or recommended use

- = not applicable or not specified

* Thickness is a general product reference and may or may not be the actual finished thickness of the product; see product data sheet.

BSR = Broad Sealing Range

VBSR = Very Broad Sealing Range

*Temperature range to achieve 300 g/25mm seal force when sealed with flat jaws at 25 N/cm² pressure and 0,5 s dwell time

**Temperature range to achieve 1,0 N/15mm seal force when sealed with flat jaws at 10 N/cm² pressure and 0,5 s dwell time

September 2025

Contact your Jindal Films representative for more information

www.jindalfilms.com

info@jindalfilms.com

Jindal
Films

© 2025 Jindal Films. Jindal Films, the Jindal Films' logo, and other product or service names used herein are trademarks of Jindal Films, unless indicated otherwise. You may not upload, display, publish, license, post, point to, frame, transmit or distribute either this document or its information, whether in whole or in part, without Jindal Films' prior written authorization. To the extent Jindal Films provides prior written authorization, the user may use the document or its information only if the document is unaltered and complete, including all of its headers, footers, disclaimers and other information. Any data included herein may be based upon: analyses of representative samples and not the actual product shipped, typical values, or otherwise. The information in this document relates only to the named product or materials when not in combination with any other product or materials. We base the information on data believed to be reliable, but we do not represent, warrant, or otherwise guarantee the accuracy, reliability, or completeness of this information; nor do we warrant, expressly or impliedly, the merchantability, fitness for a particular purpose, freedom from patent infringement, or suitability of the products, materials or processes described. The user is solely responsible for all determinations regarding any use of material or product and any process in its territories of interest. We expressly disclaim liability for any loss, damage or injury directly or indirectly suffered or incurred as a result of, or related to, anyone using or relying on any of the information in this document. This document is not an endorsement of any non-Jindal Films' product or process, and we expressly disclaim any contrary implication. The terms "we," "our," "Jindal Films" and "Jindal" are each used for convenience, and may include Films Americas LLC, Jindal Films Americas LLC, Films Europe S.à.r.l., Jindal Films Virton SPRL, Jindal Films India Ltd., or any companies affiliated with them in the production and sale of film products. There are a number of such affiliated companies, some with names including "Jindal" or "Films" and some not. Neither these terms and conditions, nor anything else in this document, is intended to override or supersede the legal separateness of those affiliated companies and responsibility for local action and accountability remains with them.